



Gasket Tape Series 1000

Datasheet

Easily and reliably seal glass-lined steel to contain aggressive media, protect equipment, and reduce emissions.


TECHNICAL SPECIFICATIONS

- Material:** 100 % expanded polytetrafluoroethylene (ePTFE) with multidirectional strength.
- Operating Range:** The maximum applicable pressure and temperature depend mainly on the equipment and installation. Typical use: from -60 °C to 230 °C (-76 °F to 445 °F) ; industrial full vacuum¹ to 10 bar (145 psi).
Maximum use: -269 °C to 315 °C (-452 °F to 600 °F); full vacuum to 16 bar (230 psi) for flanges up to DN 2000/ASME 80". Be aware that flange surface irregularities may cause high peak loads. Please contact De Dietrich if further guidance is required.
For applications outside the typical use range, Gore recommends an application specific engineering design calculation and extra care during installation.

- Chemical Resistance:** Chemical resistance to all media pH 0–14, except molten alkali metals and elemental fluorine.
- Shelf Life:** ePTFE is not subject to aging and can be stored indefinitely. To ensure optimal adhesive function, we recommend use within two years of date of purchase when stored under normal conditions.

| | Thickness | |
|---|---------------------|----------------|
| | 6 mm (1/4") | 9 mm (3/8") |
| Sealability² | | |
| Q _{min} (0.1) | 9 MPa (1,305 psi) | available soon |
| Q _{min} (0.01) | 14 MPa (2,030 psi) | available soon |
| Q _{smin} up to Lo.0001 and Q _A > 5 MPa | 5 MPa (725 psi) | available soon |
| Conformability³ | | |
| Stress to seal 0.1 mg/(m·s) measured on test plattens with a groove ³ | 9 MPa (1,305 psi) | available soon |
| Stress to seal 0.01 mg/(m·s) measured on test plattens with a groove ³ | 14 MPa (2,030 psi) | available soon |
| Creep relaxation⁴ | | |
| P _{QR} , 150 °C (302 °F) | 0.49 | available soon |
| Crush strength⁵ | | |
| Max. surface stress at 23 °C (73 °F) | 70 MPa (10,150 psi) | available soon |

Compression Curve GORE® Gasket Tape Series 1000
Tested at 23 °C (73 °F)



- 1) Absolute pressure of 1 mmHg(Torr) = 133 Pa = 1.33 mbar = 0.019 psi
- 2) Based on EN 13555 leakage test protocol. DN200 PN10 plattens, 10 bar nitrogen, 30 mm wide tape.
- 3) As 2) but with 0.5mm deep rectangular groove cut into the plattens.
- 4) Based on EN 13555 creep relaxation test protocol (P_{QR}). 2 x 250 mm x 55 mm strips, 500 kN/mm, 10 MPa starting stress.
- 5) 2 x 250 mm x 55 mm strips, 500 kN/mm, 0.1 MPa/s load rate, 15 min hold time, no visible damage.

PRODUCT SIZES

Choose tape width to be the same or wider than the width of the flange. Use 6 mm (1/4") tape thickness for deviations up to 1.5 mm (0.060"), respectively 9 mm (3/8") tape thickness for deviations up to 2.3 mm (0.090") without shimming. For greater deviations, consider shimming with GORE® Series 1000 shim tape. Further details are available in the installation instructions.

| Width | | Thickness | | Length | |
|-------|------|-----------|------|--------|-----|
| 40 mm | 1.5" | 6 mm | 1/4" | 5 m | 16' |
| 55 mm | 2" | 9 mm | 3/8" | 10 m | 32' |
| 65 mm | 2.5" | | | 15 m | 49' |

All combinations of width, thickness, and length are available. Manufactured to metric dimensions. Shim tape only available in above widths, 3 mm (1/8") thickness and 5 m (16') length.

Endorsed by **De Dietrich**
PROCESS SYSTEMS

Ask for De Dietrich expertise to help install your sealing system and take advantage of the know-how available from a leading glass-lined steel manufacturer. For more information, please visit www.dedietrich.com/en/S1000 or contact one of the following offices:

Europe/Middle East/Russia/Africa/Asia
De Dietrich Process Systems (France)
Tel.: +33 3 88 53 23 85
E-mail: aftersales@dedietrich.com

North America/South America
De Dietrich Process Systems Inc. (USA)
Tel.: +1 908 317 2585
Web: www.ddpsinc.com/S1000

China
De Dietrich Process Systems (China)
Tel.: +86 21 6390 0772
E-mail: jingyan.sun@dedietrichchina.com

FOR INDUSTRIAL USE ONLY. Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

All technical information and advice given here is based on Gore's previous experiences and/or test results. Gore gives this information to the best of its knowledge, but assumes no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. The above information is subject to change and is not to be used for specification purposes.

Gore's terms and conditions of sale apply to the sale of the products by Gore.

GORE and designs are trademarks of W. L. Gore & Associates.
© 2015 W. L. Gore & Associates GmbH

gore.com/sealants

